




FIBRIMAT F300

Technical Datasheet



PRODUCT DESCRIPTION	
Reinforcement type	Nonwoven
Process	Carding / Cross-lapping / Needlepunching
Fiber type	Flax
Packaging	Rolls: 20m x 1m

TECHNICAL DATA		
Data	Unit	Value
Areal weight	g/m ²	300 (± 10 %)
Thickness	mm	3.5 (± 1)
Molded thickness (single layer) <i>at -500 mbar</i>	mm	1.2 (± 0.1)

RECOMMENDATIONS FOR USE	
Molding process	Liquid Composite Molding process (RTM, RTM light, Infusion,...)
Reinforcement drapping	Preferential fiber direction : roll axis
Storage	Store in a dry area

Contact:

Guilherme Apolinario Testoni
Development & Technical Sales

Tel: +33 2 32 70 42 20

Email: guilherme@eco-technilin.com